

 <p>EMC Shielding Effectiveness Test Report EMI ECE Gaskets TO MIL-DTL-83528E</p>	<i>Report No.</i> 20937	<i>Issue Date</i> April 24, 2015
	<i>Revision</i> 1.0	<i>Page</i> 12 of 22

APPENDIX C - Supplemental Data

<i>Minimum</i>	<i>Best-Case</i>
<i>Attenuation Level</i>	<i>Attenuation Level</i>
<i>(dB)</i>	<i>(dB)</i>
79.3 @ 200kHz	144.1 @ 1000MHz (Material D)

Shielding Effectiveness Frequency (MHz)	Dynamic Range	815-XXXX-5519-701 (SE)
--	---------------	------------------------

20	130	125.8
30	130	128.1
40	140	137.6
60	140	135.7
80	150	143.5
100	150	138.3
200	150	144.1
400	150	140.5
600	150	138.4
800	150	143.2
1000	150	139.7
2000	125	125.7
4000	120	119.4
6000	120	119.6
8000	120	119.3
10000	120	119.5
200kHz	80	79.3