



P.O. Box 1249, 252 Brighton Rd.  
Andover, New Jersey, 07821  
Phone: 973.786-5000 Fax: 973.786-5546

### Summary of Results

<b>Applicable Specifications :</b>	MIL-DTL-83528 Rev G Type D	<b>Material:</b>	Silver Plated Aluminum Fluorosilicone	<b>Date:</b>	07/13/17
		<b>Batch # :</b>	07131719701	<b>Cure Date :</b>	3Q17

<b>Property</b>	<i>Actual</i>	<i>Actual</i>	<i>Actual</i>	<i>Required</i>
-----------------	---------------	---------------	---------------	-----------------

#### Basic Physicals

Durometer, Shore A	73	74	73	63/77
Tensile, Die C, psi	299	301	286	180 min
Tear Strength, ppi	50.25	48.02	46.39	35 min
Elongation, %	130.55	111.87	121.21	60/260
Volume Resistivity, ohm-cm	0.0025	0.0027	0.0026	.012 max
Heat Age Test, ohm-cm	0.0053	0.0057	0.0054	.015 max
Electrical Stability, ohm-cm	0.0034	0.0035	0.0036	.015 max
Specific Gravity	1.98			1.91/2.41

#### Compression Set 70 Hrs. @ 100C

% Deflection	6.30	13.28	13.39	30 max
--------------	------	-------	-------	--------

#### Supplemental Data

Manufactured in USA

Prepared By: Kimberly Calandrello  
Kimberly Calandrello  
Project technician

Approved By: Lansine Sako  
Lansine Sako  
Laboratory Manager